



PVC Double Dip Gauntlet
22733, 2734, 22833, 22834

CAT III
CE 0321

EN 420 - Sizing & Dexterity **PASS**

EN 388:2003

EN 374-3:2003

EN 374-2:2003

EN 388 - Mechanical Hazards **4-1-2-1**

Test	Abrasion	Cut	Tear	Puncture
Level	4	1	2	1



4121



AKL



EN 374-2 Air & Water Leak Tests

Air Leak Test **PASS**
Water Leak Test **PASS**

EN 374-3 Permeation Performance Levels

Measured breakthrough time in minutes.

Time	Level
10	1
>30	2
>60	3
>120	4
>240	5
>480	6

Table on right identifies which chemicals these gloves have been tested against & the level of permeation achieved.

	Chemical	Chemical Class	EN374-3 Level
A	Methanol	Primary Alcohol	3
B	Acetone	Ketone	
C	Acetonitrile	Nitrile Compound	
D	Dichloromethane	Chlorinated Paraffin	
E	Carbon Disulphide	Sulphur Containing Organic Compound	
F	Toluene	Aromatic Hydro Carbon	
G	Diethylamine	Amine	
H	Tetrahydrofuran	Heterocyclic and Ether Compound	
I	Ethyl Acetate	Ester	
J	n-Heptane	Hydrocarbon	
K	Sodium Hydroxide (40%)	Inorganic Base	6
L	Sulphuric Acid (96%)	Inorganic Mineral Acid	4
L	Hydrochloric Acid (37%)	Inorganic Mineral Acid	
L	Nitric Acid (69%)	Inorganic Mineral Acid	

USE & CARE: Always inspect your gloves before use. Cuts, tears and punctures are of principal concern. Discolouration or stiffness may indicate non-uniformities in the rubber, or may be a result of chemical attack from previous use. Any damaged gloves should be discarded and replaced prior to use.

Refer to the Chemical Resistance Guide and Physical Performance Chart (above) and select a glove with the highest rating for the chemicals and physical conditions. Always refer to the chemical label and Material Safety Data Sheet (MSDS) before use, as this may recommend a specific glove type.

The information stated in this guide is advisory only. The purchaser must determine the suitability of the glove for use with a specific chemical prior to use.

STORAGE: Keep in a cool, dry place (minimum 18°C) **DISPOSAL:** Follow EEC and UK Directives for correct disposal methods.