

Tough protection with superior wet, oily and dry grip

- Features Ansell Grip™ Technology, which minimizes force required to grip objects for reduced fatigue and increased productivity
- 80% less finger force and 33% less palm force to grip wet and dry objects, when compared to standard nitrile gloves
- Soft nitrile formulation provides comfort for long wear times
- Silicone free design is paint and finish process friendly



Industries

- Automotive Aftermarket
- Life Sciences
- Chemical

Recommended For

- General Purpose Auto Aftermarket
- Oil, fluids and filter change
- Engine transmission and repair
- Spill or leakage cleanup
- Transferring liquids and solids
- Transferring liquids
- Sample taking and processing
- Product shipping, transport and delivery
- Testing
- Maintenance



TECHNICAL DATA SHEET

PRODUCT INFORMATION

	93-250
Material	Nitrile
Color	Anthracite Grey
Glove Design	Chlorinated, Powder-Free, Textured Fingers
Cuff	Beaded
Regulatory/Standards Compliance	ASTM D6319, Category III, EAC TP TC 019:2011, EC 1935/2004, EN ISO 374-1:2016, EN 420:2003 + A1:2009, EN ISO 374-5:2016, EN 374:2003, EN 374:2003, FDA21 CFR 177-2600, ISO 9001
Packaging	100 gloves per dispenser 10 dispensers per case 1000 gloves per case
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country of Origin	Malaysia
User Needs Segment	Robust
Available sizes	XS (5.5 - 6), S (6.5 - 7), M (7.5 - 8), L (8.5 - 9), XL (9.5 - 10)
Sensitisers	<ul style="list-style-type: none"> • Zinc Dibutylthiocarbamate (ZDBC) • Zinc 2-mercaptobenzothiazole • Zinc Diethylthiocarbamate (ZDEC) <p><i>Only a very small number of users may be sensitized to this ingredient in the glove and hence may develop irritant and/or allergic contact reactions.</i></p>

PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	240 / 9.5		ASTM D3767,EN420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/mils)	0.12 / 4.7		ASTM D3767,EN420
Finger Thickness (mm/mils)	0.14 / 5.5		ASTM D3767,EN420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 36	≥ 25	ASTM D412 & D573
Elongation at Break (%)	≥ 590	≥ 520	ASTM D412
Force at break (N)	≥ 10	≥ 9	EN 455-2

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
Riverside Business Park
Blvd International, 55
1070 Brussels, Belgium
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center
(Malaysia) Sdn Bhd
Prima 6, Prima Avenue
Block 3512, Jalan Teknokrat 6
63000 Cyberjaya
Selangor, Malaysia
T: +603 8310 6688
F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC
111 Wood Avenue South,
Suite 210
Iselin, NJ 08830, USA
T: +1 800 800 0444
F: +1 800 800 0445

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.
Blvd. Bernardo Quintana No. 7001-C,
Q7001 Torre II,
Suites 1304, 1305 y 1306,
Col. Centro Sur, c.p. 76079
Queretaro, Qro. Mexico
T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited
Level 3,678 Victoria Street,
Richmond, Vic, 3121
Australia
T: +61 1800 337 041
F: +61 1800 803 578

Russia

Ahcenn PYC
123610 Poccnr, Mockba
Kpachonpechekchar
Ha6. 12, n.3, op. 1304A
Ten. +7 495 258 13 16

Technology



Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2020 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.